



ALPHA

engineered composites

145 Lehigh Avenue, Lakewood, NJ 08701
T: 732.634.5700 **F:** 732.634.1430 alphainc.com

ALPHA - ALAFLEX
 STYLE 4348 AMAU

DESCRIPTION

Alpha AlaFlex Style 4348 AMAU is a triple ply laminate made of aluminum foil, fiberglass scrim, and heat sealable metallized polyester film.

1. Foil - .00065" Aluminum
2. Adhesive - Fire Retardant, Thermo-Setting
3. Scrim - 4 x 3 fiberglass
4. Film - .0005" aluminized coextruded polyester

ADVANTAGES

Foil / Film combination provides an excellent vapor retarder.

APPLICATIONS

Flex Duct Jacketing, Vapor Retardant Facing, Pipe Jacketing.

PROPERTY DATA
 STYLE 4348 AMAU

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	2.4 oz/sy ± 10%	81.6 g/m ² ± 10%
THICKNESS	ASTM-D-1777	0.006" ± 10%	0.152 mm ± 10%
TENSILE STRENGTH	ASTM-D-5035	Warp- 30 lbs/inch Fill- 25 lbs/inch	5.36 kg/cm 4.47 kg/cm
TEAR STRENGTH	ASTM-D-1424	Warp- 24.69 oz. Fill- 17.64 oz.	700 gms. 500 gms.
BEACH PUNCTURE	ASTM-C-1136	200 units (53 inch-lbs)	6.0 joules
FLAME RESISTANCE	ASTM D-6413	Char Length 2 inch max. Afterglow 2 sec max. Flame Out 2 sec. max.	5.08 cm max. 2 sec max. 2 sec. max.
HEAT SEAL		above 200 °F	above 93.3 °C
PERMEABILITY (MVTR)	ASTM-E-96	.02 Perms	
CORROSION RESISTANCE	ASTM C-1258	120 °F @95% RH 20 days Result - No Corrosion	49 °C
TEMPERATURE RESISTANCE		-40 °F to +200 °F	-40 °C to 93 °C

DATA SHEET: 13065 REV: D DATE: 01/08/15 *All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.