



ALPHA

engineered composites

145 Lehigh Avenue, Lakewood, NJ 08701

T: 732.634.5700 F: 732.634.1430 alphainc.com

Fluoroelastomer Belt: FBT 1001

Product Description: 0.100" ; Wire Mesh/PTFE Fluoroelastomer Belt [Press Cured]

Finished Belt Requirement

Color	Black
Thickness, inches	0.100" [+/- 0.010"]
Width, inches *applies to roll goods	42" [+/- 0.5"]
Weight, Pounds/Square yard	10.0 [+/- 1.0 lb/sqyd]
Operating Temperature, Fahrenheit	450°
Gas Ply Thickness, Minimum inches	0.045"
Outer Ply Thickness, Minimum inches	0.045"

Rubber Compound Requirements

Fluoroelastomer Specification	FSA-DSJ-401-09	ASTM D-6909-10
Fluoroelastomer Content, % Volume	70% Virgin Terpolymer	
Terpolymer Fluorine Content, % Volume	68%2	
Specific Gravity, g/cm ³	1.86 [+/- 0.04]	ASTM D-297
Hardness, Durometer Shore 'A' or Equivalent	77 [+/- 5]	ASTM D-2240
Tensile Strength, Minimum PSI	1015 [7-MPa]	ASTM D-412
Elongation, Minimum	275%	ASTM D-412
Methanol Volume Swell, Maximum ¹	30%	ASTM D-471
Toluene Volume Swell, Maximum ¹	10%	ASTM D-471

¹conditions 70 +/- 0.5 hours at 23° +/- 3°C

Dry Heat Resistance²

Weight, Change	+/- 7%	ASTM D-573
Hardness, Durometer Shore 'A' Change	+/- 10	ASTM D-573
Tensile Strength, Maximum Change	+50%	ASTM D-573
Elongation, Ultimate Minimum	225%	ASTM D-573

²conditions 70 +/- 0.5 hours at 260° +/- 5°C

Wire Mesh Requirements

Weight lbs./sq.yd	1.35
Weight oz./sq.yd.	21.6
Tensile Strength (PSI)	105,000
Knit (CPI)	5.5/6.5
Elongation (Min)	25
Thickness (Inches)	0.011"

PTFE Film

Etched FEP Film 10 ml

Quality Control

Certifications and test results provided with the product at the time of shipment.

DATA SHEET: 14065 REV. B DATE: 1/15/2018

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.