



ALPHA

engineered composites

145 Lehigh Avenue, Lakewood, NJ 08701
T: 732.634.5700 **F:** 732.634.1430 alphainc.com

ALPHALAM 2001

Product Composition

	<u>English</u>	<u>Metric</u>
Fluoroplastic Chemical Barrier Compound [cast PTFE film] Custom film colors available upon request	0.004 inch	0.10mm
Coated Fiberglass Substrate	0.043 inch	1.10mm
Fluoroplastic Coating Compound	15 oz/yd ²	507 g/m ²
100% virgin PTFE resin [35% to 40% by weight]		

Physical Property

Test Method

English

Metric

Composite Weight, Nom	Basis Weight	54.0 oz/yd ²	1834 g/m ²
Composite Thickness, Nom	ASTM D1777	.047 inch	1.2mm
Tensile Strength, Min	ASTM D4851	1000 lbs/inch (MD) 1000 lbs/inch (XD)	8900 N/50mm [MD] 8900 N/50mm [XD]
Permeation Resistance ¹	ASTM F739	0.0 perm	0.0 ng/N
Trapezoidal Tear Strength, Min	ASTM D4851	50 lbs/inch (MD) 50 lbs/inch (XD)	222 N [MD] 222 N [XD]
Adhesion Strength, Min	ASTM D4851	5 lbs/inch	45 N/50mm
Flexural Endurance [-1]	ASTM D4851 60% to 100%	75% average	
Low Temperature Resistance	ASTM D1790 -75°F [-60°C]	Remains Flexible No Delamination	
High Temperature Resistance	ASTM D1790 +600°F [+316°C]	Remains Flexible No Delamination	
Water Immersion	24 hours @ 73° [23°C]	No Delamination	
Mold Resistance	ASTM C665 / C1338 ASTM G21 [both sides]	No Growth No Growth	

¹The AlphaLam composite was investigated for permeation by an independent laboratory. Sulfuric acid [2N] at 5 psig was used as the test medium. The AlphaLam composite exhibited zero breakthrough and/or permeation. Test reports available upon request.

ALPHALAM 2001 MEETS OR EXCEEDS THE REQUIREMENTS OF FSA-DSJ-403-07.

DATA SHEET: 14148 REV. A DATE: 01/01/12 * All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.