



ALPHA

engineered composites

145 Lehigh Avenue, Lakewood, NJ 08701
T: 732.634.5700 **F:** 732.634.1430 alphainc.com

ALPHA - ALAFLEX (SCRIM BASE)
 STYLE 59-M SILVER

DESCRIPTION

Alpha Style 59-M Silver is a lamination of 100% fiberglass scrim and polyester film. It is laminated using a white , high temperature-resistant, fire-retardant adhesive.

ADVANTAGES

- Resistant to oil and water
- Tough - resists damage and has excellent puncture resistance
- High tear strength

APPLICATIONS

Sound absorption membrane
 Flex Duct jacketing

PROPERTY DATA
 STYLE 59-M SILVER

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	3.0 oz/sy ± 10%	102 g/m ² ± 10%
THICKNESS	ASTM-D-1777	.008" nominal	0.203 mm nominal
TENSILE STRENGTH	ASTM-D-5035	Warp- 50 lbs/inch Fill- 50 lbs/inch	8.93 kg/cm 8.93 kg/cm
TEAR STRENGTH	ASTM-D-5587	Warp- 7 lbs Fill- 7 lbs	3.18 kg 3.18 kg
BEACH PUNCTURE	ASTM-C-1136	400 units (106 inch-lbs)	12.0 joules
FLAME RESISTANCE	ASTM D-6413	Char Length 5 1/2 inch max. Afterglow 1 sec. max. Flame Out 1 sec. max.	13.97 cm max. 1 sec. max. 1 sec. max.
PERMEABILITY (MVTR)	ASTM-E-96	Result - 0.5 Perms	
FLAME RESISTANCE	ASTME-84	FLAME SPREAD 5 SMOKE DEVELOPED 10	

Complies to U.S. Coast Guard #46 - CFR 164.012 Interior Finish
 U.S. Coast Guard Certificate of Approval 164.012/73/0
 * Contact Alpha Associates' Technical Department for paint types.

DATA SHEET: 14183 REV: A DATE: 7/15/2015 *All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.