

TDS-115 May 2019

## AVS SEWING THREAD SI3S-24/PL

## **Product Description**

**AVS Sewing Thread SI3S-24/PL** is comprised of "S-2" Fiberglass with 3 strands of Inconel Wire. **AVS Sewing Thread SI3S-24/PL** is lubricated with PTFE and silicone oil to improve handling and sewing properties.

## **Application**

**AVS Sewing Thread SI3S-24/PL** is intended for high temperature sewing applications with service temperatures up to 1400°F (760°C) for the S-2 Fiberglass and up to 2000°F (1093°C) for the Inconel wire resulting in good seam strengths. **AVS Sewing Thread SI3S-24/PL** is ideal for sewing our standard E-glass fiberglass fabrics, FLXGLAS® HT specialty treated fiberglass fabrics, AVSil® silica fabrics, and Ultisil® HT specialty silica fabrics. Fabricated textile products include removable covers, thermal wraps, tube seals, blankets, insulation pads, and curtains.

i echnicai Data	Typical Properties	value
-----------------	--------------------	-------

Construction Twisted S-2 Glass Fiber with 3 Ends Inconel Wire

Nominal Coating Level PTFE, 12%
Lubrication Silicone Oil
Nominal Diameter: inches (mm) 0.024 (0.61)

Elongation < 5%

ColorNatural/TanTensile25 lbs. min.Yield1000 yds./lb.

## NOTES:

- 1. The PTFE and Silicone oil will burn off at temperatures over 500°F (260°C)
- 2. The S-2 fiberglass will melt at temperatures over 1400°F (760°C)
- 3. The Inconel wire will maintain good strength at temperatures up to 2000°F (1093°C)
- 4. The average spool size is 2 pounds

AVS Industries cannot predict all of the potential applications for which customers may attempt to use AVS Sewing Thread SI3S-24/PL. AVS Sewing Thread SI3S-24/PL will have varying degrees of effectiveness for each potential application depending on the maximum temperature attained, the length of use, and the amount of temperature fluctuation. If the customer has any questions regarding the use of AVS Sewing Thread SI3S-24/PL in a particular application, please contact AVS Industries at (302) 221-1720 and we will provide a sample of AVS Sewing Thread SI3S-24/PL for testing. This product is not warranted against injuries or damages of any kind caused by uses for which this product was not designed, intended, or tested by AVS Industries.